


Project:  
Location:  
To:



**gA-Report**

No.: gA-62032-2020  
gA version: 1.0  
Date: 22-4-2020  
Username: VGI

**Glassadvisor GmbH Srl**  
Horazstraße 19,  
Via Orazio 19  
39100 Bozen, Bolzano (BZ)  
Italia

info@glassadvisor.com  
www.glassadvisor.com  
P.I. 02903760219



The version 1.0 of glassAdvisor has been verified by Stazione Sperimentale del Vetro and is compliant to EN673, EN410 and its Annex B.

The manufacturers of materials used in the simulation and glassAdvisor Srl can not be held responsible for any differences between the data hereby presented and those observed in reality. The spectra of the simulated materials are subject to tolerances in accordance to the relevant product standards and are subject to change without previous notice. Accessing the soft-copy version of this report may cause a recalculation of the results according to updated algorithm and/or database, the values may differ from the hardcopy. The possibility to simulate this product configuration does not guarantee the availability of the same in the market. The values are referred to the center of the glass, do not consider the effects of the edge and are executed according to one or more of the following norms and relevant attachments EN ISO 52022-3, EN673, EN410, EN13363-2 and ISO15099. The noise reduction values have a tolerance of +2dB and are obtained from a database of certification measurements supplied by producers, users or available in the market. The noise reduction estimation hereby illustrated is obtained from a certified value, through average or interpolation of two or more values and may not be used as an official certificate from a third party laboratory. Occasionally and without prior notice, glassAdvisor GmbH reserves the right to remove or update such values thus obsoleting any previous data. Copyright © - 2016 - All rights reserved - Glassadvisor GmbH

**Energy values EN410/EN673**

Ug Thermal Transmittance	0.5 W/m²K
g Solar Factor	40%
αtot Total Absorption	27%

**Light Values**

Tv Light Transmission	63%
p <sub>v</sub> External Light Reflection	23%
p <sub>v</sub> ' Internal Light Reflection	21%
Ra General Color Rendering Index	93

**Technical Data**

↔ Thickness	48.8 mm
⚖ Weight	41.9 Kg/m²
🔊 Noise Reduction [Rw(C;Ctr)dB]	37(-2;-8)

**Configuration (External -> Internal)**

4mm | GT EUROFLOAT

#2 | GT ZERO

16mm | Argon 94%

4mm | GT EUROFLOAT

#4 | GT EN2Plus

16mm | Argon 94%

4mm | GT EUROFLOAT

0.76mm | gA PVB

4mm | GT EUROFLOAT



The extensive version of this gA-Report, with more than 20 figures illustrated, may be analyzed through tablet or smartphone using this QR code, or through a desktop computer clicking on the link below.

### GENERAL INFORMATION

Standard	EN410/EN673
Glass Slope	90°
Thermal Transmittance	0.53 W/m <sup>2</sup> K
Weight	41.9 Kg/m <sup>2</sup>

### LIGHT BEHAVIOR

Light Transmittance	Tv	63%
Light Reflectance External	pv	23%
Light Reflectance Internal	pv'	21%

### SOLAR BEHAVIOR

Solar Factor	g	40%
Secondary Heat Transfer factor	qi	7%
Shading Coefficient	SC	46%
Solar Transmittance	Te	33%
Solar Reflectance	pe	41%
Absorption of Element 1	$\alpha_1$	16%
Absorption of Element 2	$\alpha_2$	6%
Absorption of Element 3	$\alpha_3$	4%
Total Absorption	$\alpha_{tot}$	27%

### UV BEHAVIOR

UV Transmittance	Tuv	0%
Material (CIE) damage factor	SMPF	37%
Skin damage factor	SSPF	1%

### SAFETY IN USE

EN12600 Resistance to impact Element 1	NPD
EN 356 Burglar Resistance Element 1	NPD
EN12600 Resistance to impact Element 2	NPD
EN 356 Burglar Resistance Element 2	NPD
EN12600 Resistance to impact Element 3	1B1
EN 356 Burglar Resistance Element 3	P2A

### COLOUR ANALYSIS

L coordinate Transmission	83.6
a coordinate Transmission	-7.9
b coordinate Transmission	4.7
RGB Transmission	196,212,199
L coordinate Reflection	55.3
a coordinate Reflection	4
b coordinate Reflection	-4
RGB Reflection	137,131,140

The color analysis is illustrative only and may slightly differ from in-situ characteristics. The boundary conditions such as wall color behind the façade, surrounding buildings and sky condition may lead to a different perception of colour in transmission and/or reflection. These colour parameters should not be used in prescription of glazing types for buildings.