


Project:
Location:
To:



gA-Report

No.: gA-62035-2020
gA version: 1.0
Date: 22-4-2020
Username: VGI

Glassadvisor GmbH Srl
Horazstraße 19,
Via Orazio 19
39100 Bozen, Bolzano (BZ)
Italia

info@glassadvisor.com
www.glassadvisor.com
P.I. 02903760219



The version 1.0 of glassAdvisor has been verified by Stazione Sperimentale del Vetro and is compliant to EN673, EN410 and its Annex B.

The manufacturers of materials used in the simulation and glassAdvisor Srl can not be held responsible for any differences between the data hereby presented and those observed in reality. The spectra of the simulated materials are subject to tolerances in accordance to the relevant product standards and are subject to change without previous notice. Accessing the soft-copy version of this report may cause a recalculation of the results according to updated algorithm and/or database, the values may differ from the hardcopy. The possibility to simulate this product configuration does not guarantee the availability of the same in the market. The values are referred to the center of the glass, do not consider the effects of the edge and are executed according to one or more of the following norms and relevant attachments EN ISO 52022-3, EN673, EN410, EN13363-2 and ISO15099. The noise reduction values have a tolerance of +2dB and are obtained from a database of certification measurements supplied by producers, users or available in the market. The noise reduction estimation hereby illustrated is obtained from a certified value, through average or interpolation of two or more values and may not be used as an official certificate from a third party laboratory. Occasionally and without prior notice, glassAdvisor GmbH reserves the right to remove or update such values thus obsoleting any previous data. Copyright © - 2016 - All rights reserved - Glassadvisor GmbH

Energy values EN410/EN673

Ug Thermal Transmittance	0.5 W/m²K
g Solar Factor	33%
atot Total Absorption	40%

Light Values

Tv Light Transmission	55%
pv External Light Reflection	28%
pv' Internal Light Reflection	28%
Ra General Color Rendering Index	90

Technical Data

↔ Thickness	53.5 mm
⚖ Weight	53.8 Kg/m²
🔊 Noise Reduction [Rw(C;Ctr)dB]	41(-2;-6)

Configuration (External -> Internal)

4mm		GT EUROFLOAT
0.76mm		gA PVB
4mm		GT EUROFLOAT
#2		GT ZERO
16mm		Argon 94%
4mm		GT EUROFLOAT
16mm		Argon 94%
#5		GT ZERO
4mm		GT EUROFLOAT
0.76mm		gA PVB
4mm		GT EUROFLOAT



The extensive version of this gA-Report, with more than 20 figures illustrated, may be analyzed through tablet or smartphone using this QR code, or through a desktop computer clicking on the link below.

GENERAL INFORMATION

Standard	EN410/EN673
Glass Slope	90°
Thermal Transmittance	0.51 W/m ² K
Weight	53.8 Kg/m ²

LIGHT BEHAVIOR

Light Transmittance	Tv	55%
Light Reflectance External	pv	28%
Light Reflectance Internal	pv'	28%

SOLAR BEHAVIOR

Solar Factor	g	33%
Secondary Heat Transfer factor	qi	7%
Shading Coefficient	SC	38%
Solar Transmittance	Te	26%
Solar Reflectance	pe	34%
Absorption of Element 1	α_1	32%
Absorption of Element 2	α_2	3%
Absorption of Element 3	α_3	5%
Total Absorption	α_{tot}	40%

UV BEHAVIOR

UV Transmittance	Tuv	0%
Material (CIE) damage factor	SMPF	30%
Skin damage factor	SSPF	0%

SAFETY IN USE

EN12600 Resistance to impact Element 1	1B1
EN 356 Burglar Resistance Element 1	P2A
EN12600 Resistance to impact Element 2	NPD
EN 356 Burglar Resistance Element 2	NPD
EN12600 Resistance to impact Element 3	1B1
EN 356 Burglar Resistance Element 3	P2A

COLOUR ANALYSIS

L coordinate Transmission	78.9
a coordinate Transmission	-10.9
b coordinate Transmission	7.4
RGB Transmission	180,201,181
L coordinate Reflection	59.7
a coordinate Reflection	3.9
b coordinate Reflection	-4.5
RGB Reflection	147,142,152

The color analysis is illustrative only and may slightly differ from in-situ characteristics. The boundary conditions such as wall color behind the façade, surrounding buildings and sky condition may lead to a different perception of colour in transmission and/or reflection. These colour parameters should not be used in prescription of glazing types for buildings.